



## TO WHOM IT MAY CONCERN

Roncello, June 2004  
Our Ref.: Wö/nf

### ACOUSTICAL PROPERTIES K-Flex ST / YOUR REQUEST

Please find copies of test results concerning above topic attached.

Also please consider some of the comments below:

1. Closed cell elastomeric foam will be, by nature, a very good sound reflector and a low efficient sound absorber. This basic characteristic will make this product ideally suitable for applications where the sound should stay "within" the system.

Examples are effluent pipe systems within a building, the running water noise should not be distributed into say, living areas.

The same is true for example for air duct systems installed in areas with public access.

2. The relevance of above is documented with test report 8125 (insertion loss index) as well as measurements undertaken in earlier years using sanitary piping systems being the origin for noise.
3. Test reports 8124 and 8203 confirm the fact that at low frequencies the sound absorption characteristics are negligible, but even acceptable at frequencies > 1kHz.

Please note that the brand names used for testing are not relevant in this case because general behaviour is being measured rather than material properties.

.../2

Results are applicable for all Kaimannflex, K-Flex or Mondoflex products.

This again suggests that if this material would be used even within an air duct, for example, it will serve its purpose being a true sound reflector with some sound absorption characteristics.

4. It is also important to note that using closed cell elastomeric foam, phenolic foam, or mineral fibre for sound absorption testing against DIN EN 20140-3 and DIN EN ISO 717-1 comparable results will be achieved.

5. As a summary for above and taking into account that the sound reduction property of a product is a function of frequency, the SOUND REDUCTION PROFILE could be stated as follows:

<b>FREQUENCY</b>	<b>(HZ)</b>	<b>250</b>	<b>500</b>	<b>1000</b>	<b>2000</b>	<b>4000</b>	<b>10000</b>
<b>NOISE REDUCTION</b>	<b>(dB)</b>	<b>10</b>	<b>23</b>	<b>30</b>	<b>33</b>	<b>35</b>	<b>50</b>

The results could be expressed as well as the *weighted* noise reduction level of 33 dB. This figure compares well with other test results available. For calculation purposes this value is normally used.

We hope that this information will be of help for you. In case further information's would be needed, don't hesitate to ask.

Kind Regards



Dr. H.P. Wöss  
Managing Director  
Isolante Service GmbH



Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Zusammenfassung von Prüfberichten Neuausfertigung Nr. 1

Lfd. Nr.	Datum	Seite
8282	13.02.2001	1 von 1

Auftraggeber: Herr Dr. Wöss  
 Isolante Service GmbH  
 Hövelmarkt 7  
 D-33161 Hövelhof

Probe/Prüfgegenstand: Elastomerschaum K-Flex ST

Probeneingang: 13.05.1996

Verteiler: Auftraggeber  
 Frau Kling (Tageskopie)  
 Vorgang 16.113  
 Vorgang 17.16.1

SAP-Nr.: 25000136

Anlagen: Prüfbericht Neuausfertigung Nr. 1  
 lfd. Nr. 8124 vom 13.02.2001, Seite 2  
 lfd. Nr. 8125 vom 13.02.2001, Seite 2 und 3  
 lfd. Nr. 8203 vom 13.02.2001, Seite 2

Prüfbezeichnung: s. Anlagen

Prüfdaten und Ergebnisse: s. Anlagen

Datum der Prüfung: s. Anlagen

Die Prüfergebnisse beziehen sich ausschließlich auf die angegebenen Prüfgegenstände bzw. Probekörper. Ohne schriftliche Genehmigung des Prüflaboratoriums Physikalische Prüfungen darf der Prüfbericht, auch auszugsweise, nicht vervielfältigt werden.

Gegenüber der lfd. Nr. 8282 vom 10.10.1996 wurde die Adresse und die Materialbezeichnung geändert.

Dipl.-Ing. E. Buhl  
 Tel. (06201) 80-4104



Authenticated translation from the German language  
=====

# Freudenberg Forschungsdienste KG (Freudenberg Research Services)

## Test Laboratory for Physical Tests

### Summary of Test Reports New Edition No. 1

Current No.	Date	Page
8282	February 13, 2001	1 of 1

Client: Dr. H.-P. Wöss  
Isolante Service GmbH  
Hövelmarkt 7

33161 Hövelmarkt

Sample / Material to be tested: Elastomer foam K-Flex ST

Date when the samples were received: May 13, 1996

Distribution: Client  
Ms. Kling (copy)  
Correspondence 16.113  
Correspondence 17.16.1

SAP-No. 25000136

Annexes: Test report new edition No. 1  
- Serial No. 8124 dated February 13, 2001, page 2  
- Serial No. 8125 dated February 13, 2001, page 2 and 3  
- Serial No. 8203 dated February 13, 2001, page 2

Test designation: See Annexes

Test data and results: See Annexes

Date of the test: See Annexes

The test results and statements of the tests refer exclusively to the above-mentioned samples or test objects resp. The publication of this Test Report (also in excerpts) requires the prior written approval of the Test Laboratory for Physical Material Testing.

In comparison to the Serial No. 8282 dated October 10, 1996, the address and the designation of the material were altered.

(signed) (signature) Dipl.-Ing. E. Buhl - +49 (0) 6201 / 80-4104



=====  
Certified that this is a complete and faithful translation from the German language

26524 Hage, July 05, 2002

Sworn translator and interpreter for the English language for the courts of the District of the Regional Court Aurich



*Paul Hohenadel*



Reg.Nr. 4331-04


DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht Neuausfertigung Nr. 1

Lfd. Nr.	Datum	Prüfer	Telefon	Seite
8124	13.02.2001	Hechler	4460	2 von 2


Aufbau des Prüfgegenstands (Randabdichtung mit Vaseline) :



Elastomerschaum K-Flex ST, ca. 12,6 mm dick  
Flächengewicht ca. 0,84 kg/m<sup>2</sup>

Probekörper mit doppelseitigem Klebeband  
auf den Abschluss des Kundt-Rohrs geklebt.

Versuch Nr.	1624	Kurve	A	B
Prüfdatum	14.05.1996	Rohrlänge	100 cm	30 cm
Prüfklima	19°C, 32% r.F.	Rohrquerschnitt	77 cm <sup>2</sup>	6,6 cm <sup>2</sup>





Authenticated translation from the German language

=====

# Freudenberg Forschungsdienste KG (Freudenberg Research Services)

## Test Laboratory for Physical Tests

Test Report New Edition No. 1

Serial No.	Date	Tester	Telephone	Page
8124	February 13, 2001	Hechler	4460	2 of 2

Installation of the object to be tested (edge sealing with vaseline)

Elastomer foam K-Flex ST, approx. 12.6 mm thick,  
Area weight approx. 0.84 kg/m<sup>2</sup>

Test piece with double-sided adhesive tape  
Sticking to the closure of the Kundt tube

Test No.	1624	Curve	A	B
Test date	May 14, 1996	Tube length	100 cm	30cm
Test climate	19 °C, 32%r.h.	Tube cross section	77 cm	6.6 cm

Sound absorption  
factor

Frequency in Hz

=====

Certified that this is a complete and faithful translation from the German language

26524 Hage, July 05, 2002

Sworn translator and interpreter for the English language for the courts  
of the District of the Regional Court Aurich





Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht Neuausfertigung Nr. 1


Lfd. Nr.	Datum	Prüfer	Telefon	Seite
8125	13.02.2001	Hechler	4460	2 von 3

#### Aufbau des Prüfgegenstands:

Dauerplastische  
Abdichtung (Terostat IX)

Prüfplatte, ca. 400mm x 400mm, bestehend aus:

Verzinktes Stahlblech, 1,25 mm dick  
Elastomerschaumplatte K-Flex ST, ca. 12,5 mm dick  
Verklebung mit K-Flex K414 Spezialkleber  
Gesamt-Flächengewicht ca. 10,3 kg/m<sup>2</sup>  
Elastomerschaum zur Schallquelle gerichtet



Prüföffnung 360mm x 360mm  
Dämmkisten-Abdeckung aus Rigipsplatten,  
mit Mineralwolle gefüllt

Schaumgummidichtung  
Stahlblech, 2 mm dick  
Frelen-Flockenfüllung, 70 mm  
Tischlerplatte, 22 mm dick

#### Prüfdaten:

Versuch Nr.	4712 und 4714
Prüfdatum	3.06.1996
Prüfklima	18°C, 67% r.F.
Prüfapparatur	Schalldämm-Messvorrichtung für den horizontalen Einbau von Dämmplatten ("Dämmkiste")
Aufstellungsort	Nord-Ost-Ecke des Hallraums K15, Wandabstand ca. 1,2 m
Schallquelle	Kugelmühle mit einer Drehzahl von 62 U/min in der Dämmkiste
Empfangsgerät	GenRad-Echtzeitanalysator Typ 1995, Terzpegel, Mittelungszeit 10 s
Mikrofon	GenRad-1/2" in der Hallraum-Mikrofon-Stellung 4





Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht Neuausfertigung Nr. 1


Lfd. Nr.	Datum	Prüfer	Telefon	Seite
8125	13.02.2001	Hechler	4460	3 von 3

#### Ergebnisse:

Das Einfügungsdämm-Maß (Schallpegel-Differenz zwischen der offenen und der mit Dämmmaterial abgedeckten Dämmkiste) in Abhängigkeit der Terz-Mittenfrequenz im Bereich 315 Hz bis 16 kHz ist im folgenden Diagramm graphisch dargestellt.

Terz-Mittenfrequenz in Hz	Einfüg.-Dämm-Maß in dB
315	9,5
400	11,5
500	23,0
630	24,6
800	26,5
1000	29,3
1250	31,8
1600	32,3
2000	33,7
2500	34,0
3150	34,0
4000	36,0
5000	38,8
6300	43,0
8000	46,5
10000	49,8
12500	50,3
16000	48,4

Stahlblech mit Elastomerschaum K-Flex ST





Authenticated translation from the German language  
=====

# Freudenberg Forschungsdienste KG (Freudenberg Research Services)

## Test Laboratory for Physical Tests

Test Report New Edition No. 1

Serial No.	Date	Tester	Telephone	Page
8125	February 13, 2001	Hechler	4460	2 of 3

### Installation of the object to be tested

Permanently plastic sealing (Terostat IX)

Test plate, approx. 400 mm x 400 mm, consisting of  
Zinc coated steel plate, 1.25 mm thick,  
Elastomer foam plate K-Flex ST, approx. 12.5 mm thick  
Adhesion with K-Flex K414 special adhesive,  
Total area weight approx. 10.3 kg/m<sup>2</sup>  
Elastomer foam pointed to the sound source

Test opening 360 mm x 360 mm  
Insulating box cover consisting of rigips plates,  
filled with mineral wool

Foam rubber sealing  
Steel plate, 2 mm thick  
Frelen flake filling, 70 mm  
Wood core plywood, 200 mm thick

### Test data:

Test No.:	4712 and 4714
Test date:	June 03, 1996
Test climate:	18 °C, 67 % rel. humidity
Test apparatus:	Sound insulation measuring apparatus for the horizontal arrangement of insulation plates ("insulating box")
Place of arrangement:	North-east corner of the echo room K15, Wall distance approx. 1.2 m
Sound source:	Ball mill with a rotation of 62 Rpm in the insulating box
Receiving device:	GenWheel real time analyzer Type 1995, Third level, communication period of time 10 sec
Microphone:	GenWheel-1/2" in the echo room microphone position 4

Freudenberg Forschungsdienste KG  
(Freudenberg Research Services)



Test Laboratory for Physical Tests


Test Report

Serial No.	Date	Tester	Telephone	Page
8125	February 13, 2001	Hechler	4460	3 of 3

Results:

The insertion insulation factor (sound level difference between the open and the insulation box covered by insulation material) depending on the third medium frequency in the range 315 Hz to 16 kHz is graphically displayed in the following diagram:

Third medium frequency	Insertion insulating factor in dB	Steel plate with Elastomer foam K-Flex ST
------------------------	-----------------------------------	---



=====  
Certified that this is a complete and faithful translation from the German language

26524 Hage, July 05, 2002

Sworn translator and interpreter for the English language for the courts of the District of the Regional Court Aurich





Reg.Nr. 4331-04


DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht Neuausfertigung Nr. 1

Lfd. Nr.	Datum	Prüfer	Telefon	Seite
8203	13.02.2001	Hechler	4460	2 von 2


**Aufbau des Prüfgegenstands (Randabdichtung mit Vaseline):**



Elastomerschaum K-Flex ST, ca. 12,6 mm dick  
Flächengewicht ca. 0,84 kg/m<sup>2</sup>

Probekörper mit doppelseitigem Klebeband  
auf den Abschluss des Kundt-Rohrs geklebt.

Versuch Nr.	1625	Kurve	A	B
Prüfdatum	22.07.1996	Rohrlänge	100 cm	30 cm
Prüfklima	22°C, 41% r.F.	Rohrquerschnitt	77 cm <sup>2</sup>	6,6 cm <sup>2</sup>





Authenticated translation from the German language

=====

Freudenberg Forschungsdienste KG  
(Freudenberg Research Services)

Test Laboratory for Physical Tests

Test Report New Edition No. 1

Serial No.	Date	Tester	Telephone	Page
8203	February 13, 2001	Hechler	4460	2 of 2

Installation of the object to be tested

Elastomer foam plate K-Flex ST, approx. 12.5 mm thick  
Area weight approx. 0.84 kg/m<sup>2</sup>

Test piece with double-sided adhesion tape  
sticking to the closure of the Kundt tube

Test No.	1625	Curve	A	B
Test date	July 22, 1996	Tube length	100 cm	30cm
Test climate	22 °C, 41%r.h.	Tube cross section	77 cm	6.6 cm

Sound absorption  
factor

Frequency in Hz

=====

Certified that this is a complete and faithful translation from the German language

26524 Hage, July 05, 2002

Sworn translator and interpreter for the English language for the courts  
of the District of the Regional Court Aurich





Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

Lfd. Nr.	Datum	Seite
2883	5.02.2001	1 von 3

Auftraggeber: Herr Dr. Wöss  
Isolante Service GmbH  
Hövelmarkt 7  
D-33161 Hövelhof

Probe/Prüfgegenstand: 1 Prüfplatte, ca. 600mm x 600mm,  
Stahlblech mit K-Flex ST,  
Aufbau des Prüfgegenstands s. Seite 2

Probeneingang: 6.10.2000

Verteiler: Auftraggeber  
Frau Kling (Tageskopie)  
Vorgang 16.144  
Protokolle

SAP-Nr.: 10000660

Prüfbezeichnung: Luftschalldämmung im Prüfstand  
mit bauähnlicher Flankenübertragung  
DIN EN 20140-3: 1995-05 und  
DIN EN ISO 717-1: 1997-01

Prüfdaten und Ergebnisse: s. Seite 2 und 3

Datum der Prüfung: 14.11.2000

Die Prüfergebnisse beziehen sich ausschließlich auf die angegebenen Prüfgegenstände bzw. Probekörper. Ohne schriftliche Genehmigung des Prüflaboratoriums Physikalische Prüfungen darf der Prüfbericht, auch auszugsweise, nicht vervielfältigt werden.



Dipl.-Ing. E. Buhl  
Tel. (06201) 80-4104



Reg.Nr. 4331-04


DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

Lfd. Nr.	Datum	Prüfer	Telefon	Seite
2883	5.02.2001	Ehwald <i>el.</i>	4460	2 von 3

### Aufbau des Prüfgegenstands:



### Prüfdaten:

Versuch Nr.	5305	
Probengröße in mm	ca. 600 x 600	
Prüffläche S in m <sup>2</sup>	0,36	
Prüfräume	Senderraum	Empfangsraum
Volumen V in m <sup>3</sup>	133	63
Zustand	leer	leer
Prüfstand	Hallraum K15	Hallraum K16
Klima	20°C, 68% r.F.	20°C, 68% r.F.
Trennwand	Stahlbeton, ca. 0,5 m dick	
Breite x Höhe in m	ca. 4,52 x 2,79	
Fläche in m <sup>2</sup>	ca. 12,61	
Prüföffnung	in der Trennwand	
Breite x Höhe in m	ca. 1,0 x 2,0	



Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

<b>Lfd. Nr.</b> 2883	<b>Datum</b> 5.02.2001	<b>Prüfer</b> Ehwald <i>fl.</i>	<b>Telefon</b> 4460	<b>Seite</b> 3 von 3
-------------------------	---------------------------	------------------------------------	------------------------	-------------------------

### Ergebnisse:

Bewertetes Schalldämm-Maß

$R'_w = 35$  dB

Spektrum-Anpassungswert


$C = -2$  dB

Spektrum-Anpassungswert

$C_{tr} = -5$  dB

### Stahlblech mit K-Flex ST

f in Hz	R' in dB
100	15,1
125	21,9
160	21,8
200	26,3
250	29,6
315	30,7
400	29,9
500	29,1
630	27,0
800	29,5
1000	35,5
1250	40,5
1600	44,7
2000	48,2
2500	51,2
3150	51,9
4000	56,3
5000	56,9



f Terz-Mittenfrequenz  
R' Schalldämm-Maß





Authenticated translation from the German language



# Freudenberg Forschungsdienste KG (Freudenberg Research Services)

## Test Laboratory for Physical Tests

### Test Report

Current No.	Date	Page
2883	February 05, 2001	1 of 3

Client: Dr. H.-P. Wöss  
Isolante Service GmbH  
Hövelmarkt 7

33161 Hövelmarkt

Sample / Material to be tested: 1 Test plate, approx. 600mm x 600mm,

Steel plate with K-Flex ST,  
For installation of the object to be tested, see page 2

Date when the samples were received: October 06, 2000

Distribution: Client  
Ms. Kling (copy)  
Correspondence 16.144  
Protocols

SAP-No. 10000660

Designation of samples: Airborne sound insulation in the test bed with similar structural edge transmission  
DIN EN 20140-3; 1995-05 and  
DIN EN ISO 717-1; 1997-01

Test data and results: Pages 2 and 3

Date of test: November 14, 2000

The test results and statements of the tests refer exclusively to the above-mentioned samples or test objects resp. The publication of this Test Report (also in excerpts) requires the prior written approval of the Test Laboratory for Physical Material Testing.

(signed) (signature) Dipl.-Ing. E. Buhl - +49 (0) 6201 / 80-4104



# Freudenberg Forschungsdienste KG (Freudenberg Research Services)

## Test Laboratory for Physical Tests

### Test Report

Current No.	Date	Tester	Telephone	Page
2883	February 05, 2001	Ehwald	4460	2 of 3

### Installation of the object to be tested

Fastening of the object to be tested  
in the test opening

Rigips plate, approx. 13 mm thick  
mineral fiber mat, approx. 40 mm thick  
air space, approx. 30 mm  
rubber sealing, approx. 4 mm thick  
permanent plastic sealing (Terostat IX)

Broad-  
casting  
studio

Re-  
ceiving  
studio

Steel plate, approx. 600 x 600 mm, 1.5 mm thick  
K-Flex ST, approx. 600 x 600 mm, 50 mm thick  
K-Flex ST was pasted on by adhesion to the steel plate  
Total area weight approx. 14.8 kg/m<sup>2</sup>

### Test data:

Test No.	5305	
Sample size in mm	Approx. 600 x 600	
Test area S in m <sup>2</sup>	0.36	
Test rooms	Transmission room	Receiving room
- Volume V in m <sup>3</sup>	133	63
- Condition	empty	empty
- Testing room	Echo chamber K 15	Echo chamber K 16
- Climate	20 °C, 68 % rel. humidity	20 °C, 68 % rel. humidity
Dividing wall	Reinforced concrete, approx. 0.5 m thick	
- Width x height in m	approx. 4.52 x 2.79	
- Area in m <sup>2</sup>	approx. 12.61	
Test opening	in the dividing wall	
- Width x height in m	approx. 1.0 x 2.0	



Freudenberg Forschungsdienste KG  
(Freudenberg Research Services)

Test Laboratory for Physical Tests

Test Report

Current No. 2883      Date February 05, 2001      Tester Ehwald      Telephone 4460      Page 3 of 3

Results:

Sound insulation factor assessed       $R'_w =$       35      dB  
 Spectrum adaptation value       $C =$       -2      dB  
 Spectrum adaptation value       $C_{tr}$       -5      dB

Steel plate with K-Flex ST

F in Hz	R' in dB	Sound insulation factor		

Frequency in Hz

f Third center frequency  
 R' Sound insulation factor

=====  
 Certified that this is a complete and faithful translation from the German language

26524 Hage, July 05, 2002

Sworn translator and interpreter for the English language for the courts of the District of the Regional Court Aurich





Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

Lfd. Nr.	Datum	Seite
2883.1	5.02.2001	1 von 3

Auftraggeber: Herr Dr. Wöss  
Isolante Service GmbH  
Hövelmarkt 7  
D-33161 Hövelhof

Probe/Prüfgegenstand: 1 Prüfplatte, ca. 600mm x 600mm,  
Stahlblech mit Phenolharz-Hartschaumplatte,  
Aufbau des Prüfgegenstands s. Seite 2

Probeneingang: 27.10.2000

Verteiler: Auftraggeber  
Frau Kling (Tageskopie)  
Vorgang 16.144  
Protokolle

SAP-Nr.: 10000660

Prüfbezeichnung: Luftschalldämmung im Prüfstand  
mit bauähnlicher Flankenübertragung  
DIN EN 20140-3: 1995-05 und  
DIN EN ISO 717-1: 1997-01

Prüfdaten und Ergebnisse: s. Seite 2 und 3

Datum der Prüfung: 15.11.2000

Die Prüfergebnisse beziehen sich ausschließlich auf die angegebenen Prüfgegenstände bzw. Probekörper. Ohne schriftliche Genehmigung des Prüflaboratoriums Physikalische Prüfungen darf der Prüfbericht, auch auszugsweise, nicht vervielfältigt werden.



Dipl.-Ing. E. Buhl  
Tel. (06201) 80-4104



Reg.Nr. 4331-04


DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

Lfd. Nr.	Datum	Prüfer	Telefon	Seite
2883.1	5.02.2001	Ehwald <i>Ph.</i>	4460	2 von 3

### Aufbau des Prüfgegenstands:



Halterung des Prüfgegenstands  
in der Prüföffnung:

- Rigipsplatte, ca. 13 mm dick
- Mineralfasermatte, ca. 40 mm dick
- Luftraum, ca. 30 mm
- Gummidichtung, ca. 4 mm dick
- Dauerplastische Abdichtung (Terostat IX)
- Stahlblech, ca. 600 x 600 mm, 1,5 mm dick
- Phenolharz-Hartschaumplatte, ca. 600 x 600 mm, 43 mm dick, beidseitig mit Al-beschichtetem Papier, ca. 0,1 mm dick, kaschiert.
- Phenolharzplatte mit doppelseitigem Klebeband auf das Stahlblech geklebt.
- Gesamt-Flächengewicht ca. 13,5 kg/m<sup>2</sup>

### Prüfdaten:

Versuch Nr.	5306	
Probengröße in mm	ca. 600 x 600	
Prüffläche S in m <sup>2</sup>	0,36	
Prüfräume	Senderraum	Empfangsraum
Volumen V in m <sup>3</sup>	133	63
Zustand	leer	leer
Prüfstand	Hallraum K15	Hallraum K16
Klima	20°C, 61% r.F.	20°C, 61% r.F.
Trennwand	Stahlbeton, ca. 0,5 m dick	
Breite x Höhe in m	ca. 4,52 x 2,79	
Fläche in m <sup>2</sup>	ca. 12,61	
Prüföffnung	in der Trennwand	
Breite x Höhe in m	ca. 1,0 x 2,0	



Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

<b>Lfd. Nr.</b>	<b>Datum</b>	<b>Prüfer</b>	<b>Telefon</b>	<b>Seite</b>
2883.1	5.02.2001	Ehwald <i>Dr.</i>	4460	3 von 3

### Ergebnisse:

Bewertetes Schalldämm-Maß

$R'_w =$	<b>35</b>	<b>dB</b>
----------	-----------	-----------

Spektrum-Anpassungswert


$C =$  -2 dB

Spektrum-Anpassungswert

$C_{tr} =$  -5 dB

Stahlblech mit Phenolharz-Hartschaumplatte

f in Hz	R' in dB
100	14,9
125	19,5
160	22,8
200	27,1
250	28,3
315	31,0
400	32,1
500	32,3
630	31,6
800	33,6
1000	35,1
1250	36,4
1600	36,7
2000	36,5
2500	36,0
3150	36,2
4000	42,3
5000	49,5



f Terz-Mittenfrequenz  
R' Schalldämm-Maß



Authenticated translation from the German language  
=====



## Freudenberg Forschungsdienste KG (Freudenberg Research Services)

### Test Laboratory for Physical Tests

#### Test Report

Current No.	Date	Page
28831	February 05, 2001	1 of 3

Client: Dr. H.-P. Wöss  
Isolante Service GmbH  
Hövelmarkt 7

33161 Hövelmarkt

Sample / Material to be tested: 1 Test plate, approx. 600mm x 600mm,  
Steel plate with phenolic resin high-resistance foam plate  
For installation of the object to be tested, see page 2

Date when the samples were received: October 27, 2000

Distribution: Client  
Ms. Kling (copy)  
Correspondence 16.144  
Protocols

SAP-No. 10000660

Designation of samples: Airborne sound insulation in the test bed  
with similar structural edge transmission  
DIN EN 20140-3; 1995-05 and  
DIN EN ISO 717-1; 1997-01

Test data and results: Pages 2 and 3

Date of test: November 15, 2000

The test results and statements of the tests refer exclusively to the above-mentioned samples or test objects resp. The publication of this Test Report (also in excerpts) requires the prior written approval of the Test Laboratory for Physical Material Testing.

(signed) (signature) Dipl.-Ing. E. Buhl – Tel. +49 (0)6202 / 80-4104



Freudenberg Forschungsdienste KG  
(Freudenberg Research Services)

Test Laboratory for Physical Tests

Test Report

Current No. 2883.1	Date February 05, 2001	Tester Ehwald	Telephone 4460	Page 2 of 3
-----------------------	---------------------------	------------------	-------------------	----------------

Installation of the object to be tested

Fastening of the object to be tested  
in the test opening

Rigips plate, approx. 13 mm thick  
mineral fiber mat, approx. 40-mm thick  
air space, approx. 30 mm  
rubber sealing, approx. 4 mm thick  
permanent plastic sealing (Terostat IX)

Steel plate, approx. 600 x 600 mm, 1.5 mm thick  
Phenolic resin high-resistance foam plate, approx. 600 x  
600 mm, 43 mm thick  
on both sides with aluminum coated paper,  
approx. 0.1 mm thick, paste lined  
Phenolic resin plate with double-sided adhesive tape  
pasted to the steel plate  
Total area weight approx. 13.5 kg/m<sup>2</sup>

Broadcasting  
studio

Receiving studio

Test data:

Test No.	5306	
Sample size in mm	Approx. 600 x 600	
Test area S in m <sup>2</sup>	0.36	
Test rooms	Transmission room	Receiving room
- Volume V in m <sup>3</sup>	133	63
- Condition	empty	empty
- Testing room	Echo chamber K 15	Echo chamber K 16
- Climate	20 °C, 61 % rel. humidity	20 °C, 61 % rel. humidity
Dividing wall	Reinforced concrete, approx. 0.5 m thick	
- Width x height in m	approx. 4.52 x 2.79	
- Area in m <sup>2</sup>	approx. 12.61	
Test opening	in the dividing wall	
- Width x height in m	approx. 1.0 x 2.0	



Freudenberg Forschungsdienste KG  
(Freudenberg Research Services)



Test Laboratory for Physical Tests

Test Report

Current No. 2883      Date February 05, 2001      Tester Ehwald      Telephone 4460      Page 3 of 3

Results:

Sound insulation factor assessed       $R'_w =$       35      dB  
 Spectrum adaptation value       $C =$       -2      dB  
 Spectrum adaptation value       $C_{tr}$       -5      dB

Steel plate with K-Flex ST

F in Hz	R' in dB	Sound insulation factor		

f Third center frequency      Frequency in Hz  
 R' Sound insulation factor

=====  
 Certified that this is a complete and faithful translation from the German language

26524 Hage, July 05, 2002 *Paul Hohenadel*

Sworn translator and interpreter for the English language for the courts of the District of the Regional Court Aurich





Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

Lfd. Nr.	Datum	Seite
2883.2	5.02.2001	1 von 3

Auftraggeber: Herr Dr. Wöss  
Isolante Service GmbH  
Hövelmarkt 7  
D-33161 Hövelhof

Probe/Prüfgegenstand: 1 Prüfplatte, ca. 600mm x 600mm,  
Stahlblech mit Mineralfasermatte,  
Aufbau des Prüfgegenstands s. Seite 2

Probeneingang: 30.11.2000

Verteiler: Auftraggeber  
Frau Kling (Tageskopie)  
Vorgang 16.144  
Protokolle

SAP-Nr.: 10000660

Prüfbezeichnung: Luftschalldämmung im Prüfstand  
mit bauähnlicher Flankenübertragung  
DIN EN 20140-3: 1995-05 und  
DIN EN ISO 717-1: 1997-01

Prüfdaten und Ergebnisse: s. Seite 2 und 3

Datum der Prüfung: 12.01.2001

Die Prüfergebnisse beziehen sich ausschließlich auf die angegebenen Prüfgegenstände bzw. Probekörper. Ohne schriftliche Genehmigung des Prüflaboratoriums Physikalische Prüfungen darf der Prüfbericht, auch auszugsweise, nicht vervielfältigt werden.



Dipl.-Ing. E. Buhl  
Tel. (06201) 80-4104



Reg.Nr. 4331-04


DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

Lfd. Nr.	Datum	Prüfer	Telefon	Seite
2883.2	5.02.2001	Ehwald <i>Elu</i>	4460	2 von 3

### Aufbau des Prüfgegenstands:



### Prüfdaten:

Versuch Nr.	5307	
Probengröße in mm	ca. 600 x 600	
Prüffläche S in m <sup>2</sup>	0,36	
Prüfräume	Senderraum	Empfangsraum
Volumen V in m <sup>3</sup>	133	63
Zustand	leer	leer
Prüfstand	Hallraum K15	Hallraum K16
Klima	19°C, 57% r.F.	19°C, 57% r.F.
Trennwand	Stahlbeton, ca. 0,5 m dick	
Breite x Höhe in m	ca. 4,52 x 2,79	
Fläche in m <sup>2</sup>	ca. 12,61	
Prüföffnung	in der Trennwand	
Breite x Höhe in m	ca. 1,0 x 2,0	



Reg.Nr. 4331-04

DAP-P-02.164-00-99-01

## Prüflaboratorium Physikalische Prüfungen

### Prüfbericht

<b>Lfd. Nr.</b> 2883.2	<b>Datum</b> 5.02.2001	<b>Prüfer</b> Ehwald <i>fl.</i>	<b>Telefon</b> 4460	<b>Seite</b> 3 von 3
---------------------------	---------------------------	------------------------------------	------------------------	-------------------------

### Ergebnisse:

Bewertetes Schalldämm-Maß

$R'_w =$	<b>36</b>	<b>dB</b>
----------	-----------	-----------

Spektrum-Anpassungswert


$C =$  -1 dB

Spektrum-Anpassungswert

$C_{tr} =$  -5 dB

Stahlblech mit Mineralfasermatte

f in Hz	R' in dB
100	18,5
125	22,6
160	21,7
200	23,8
250	27,8
315	30,2
400	29,9
500	31,9
630	33,2
800	34,5
1000	37,8
1250	39,6
1600	41,6
2000	43,6
2500	45,6
3150	46,5
4000	47,6
5000	44,4



f Terz-Mittenfrequenz

R' Schalldämm-Maß



Authenticated translation from the German language  
=====

# Freudenberg Forschungsdienste KG (Freudenberg Research Services)

## Test Laboratory for Physical Tests

### Test Report

Current No.                      Date                                      Page  
2883.2                              February 05, 2001                      1 of 3

Client:                              Dr. H.-P. Wöss  
    Isolante Service GmbH  
    Hövelmarkt 7

33161 Hövelmarkt

Sample / Material to be tested:      1 Test plate, approx. 600mm x 600mm,  
    Steel plate with mineral fiber mat  
    For installation of the object to be tested, see page 2

Date when the samples were received:      November 30, 2000

Distribution:                      Client  
    Ms. Kling (copy)  
    Correspondence 16.144  
    Protocols

SAP-No.                              10000660

Designation of samples:      Airborne sound insulation  
    with similar structural edge transmission  
    DIN EN 20140-3; 1995-05 and  
    DIN EN ISO 717-1; 1997-01

Test data and results:              Pages 2 and 3

Date of test:                              January 12, 2001

The test results and statements of the tests refer exclusively to the above-mentioned samples or test objects resp. The publication of this Test Report (also in excerpts) requires the prior written approval of the Test Laboratory for Physical Material Testing.

(signed) (signature) Dipl.-Ing. E. Buhl – Tel. +49 (o) 6201 / 80-4104



# Freudenberg Forschungsdienste KG (Freudenberg Research Services)

## Test Laboratory for Physical Tests

### Test Report

Current No.	Date	Tester	Telephone	Page
2883.2	February 05, 2001	Ehwald	4460	2 of 3

### Installation of the object to be tested

Fastening of the object to be tested  
in the test opening

Rigips plate, approx. 13 mm thick  
mineral fiber mat, approx. 40-mm thick  
air space, approx. 30 mm  
rubber sealing, approx. 4 mm thick  
permanent plastic sealing (Terostat IX)

Steel plate, approx. 600 x 600 mm, 1.5 mm thick  
mineral fiber mat, approx. 600 x 600 mm, 50 mm thick  
Volume weight approx. 15 kg/m<sup>3</sup>  
The mineral fiber mat was pasted on to the steel plate by  
means of double-sided adhesive tape  
Total area weight approx. 11.8 kg/m<sup>2</sup>

Broadcasting  
studio

Receiving  
studio

### Test data:

Test No.	5305	
Sample size in mm	Approx. 600 x 600	
Test area S in m <sup>2</sup>	0.36	
Test rooms	Transmission room	Receiving room
- Volume V in m <sup>3</sup>	133	63
- Condition	empty	empty
- Testing room	Echo chamber K 15	Echo chamber K 16
- Climate	19 °C, 57 % rel. humidity	19 °C, 57 % rel. humidity
Dividing wall	Reinforced concrete, approx. 0.5 m thick	
- Width x height in m	approx. 4.52 x 2.79	
- Area in m <sup>2</sup>	approx. 12.61	
Test opening	in the dividing wall	
- Width x height in m	approx. 1.0 x 2.0	



Freudenberg Forschungsdienste KG  
(Freudenberg Research Services)

Test Laboratory for Physical Tests

Test Report

Current No. 2883.2	Date February 05, 2001	Tester Ehwald	Telephone 4460	Page 3 of 3
-----------------------	---------------------------	------------------	-------------------	----------------


Results:

Sound insulation factor assessed	$R'_w =$	35	dB
Spectrum adaptation value	$C =$	-1	dB
Spectrum adaptation value	$C_{tr}$	-5	dB

Steel plate with K-Flex ST
----------------------------

f in Hz	R' in dB	Sound insulation factor		

f Third center frequency  
R' Sound insulation factor



Certified that this is a complete and faithful translation from the German language

26524 Hage, July 05, 2002

*Paul Hohenadel*

Sworn translator and interpreter for the English language for the courts of the District of the Regional Court Aurich

